



STANDARD

CLASSIFICATION

FEATURES

UNI EN 10263-2: 2017

Heat treatable steels, alloy steels and free-cuttings steels - non alloy steels for quencing and tempering

Non Alloy Quality Steel

C8C - Nr. 1.0213

Steels with average 0,25% = < C < 0,55% or 500 MPa
=< Rm < 700 MPa

CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,08 to 0,12	0,10 max	from 0,30 to 0,50	0,02 max	0,025 max	-	-
Mo	Ni	B	Cu	Al	Pb	
-	-	-	-	from 0,020 to 0,060	-	

MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	5	-	-	-	-	-	-	350	72	390	68	-	-
5	10	410	65	360	70	490	63	340	72	380	68	450	65
10	40	410	65	360	70	480	63	340	72	380	68	450	65
40	100	410	65	360	70	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C8C	QST34-3	-	-	-	-	-
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
-	-	-	-	-	-	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.