



## STANDARD

## CLASSIFICATION

## FEATURES

**UNI EN ISO 16120-2:2017**

**C10D - Nr. 1.0310**

Non Alloy Steel Wire Rod For Conversion to Wire - rimmed and rimmed substitute, low-carbon steel wire rod

*Non-alloy low carbon steel*

Structural pressure vessel and engineering steels with C < 0,5%

## CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,08 to 0,13	0,30 max	from 0,30 to 0,60	0,035 max	0,035 max	0,20 max	-
Mo	Ni	B	Cu	Al	Pb	
0,05 max	0,25 max	-	0,30 max	0,01 max	-	

## MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	60	-	-	-	-	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

## EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C10D	C10D	FM 10	C 10 D	-	-	-
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
1010	SWRM 10	-	-	-	10	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.