



STANDARD

CLASSIFICATION

FEATURES

UNI EN 10263-2: 2017

C17C - Nr. 1.0434

Non Alloy Steel Wire Rod For Conversion to Wire - general purpose wire rod

Non Alloy Steel

Steels with average 0,25% = < C < 0,55% or 500 MPa
=< Rm < 700 MPa

CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,15 to 0,19	0,10 max	from 0,65 to 0,85	0,025 max	0,025 max	-	-
Mo	Ni	B	Cu	Al	Pb	
-	-	-	-	from 0,020 to 0,060	-	

MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	5	-	-	-	-	-	-	430	67	470	63	-	-
5	10	520	58	440	65	610	56	420	67	460	63	530	60
10	40	520	58	440	65	600	56	420	67	460	63	520	60
40	100	520	58	440	65	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C17C	-	-	-	-	-	-
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
-	-	-	-	-	-	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.