



STANDARD

CLASSIFICATION

FEATURES

UNI EN ISO 683-1: 2018

Alloy special steel

C40 - Nr. 1.0511

Steel rods, bars and wire for cold heading and cold extrusion - steels for quenching and tempering

B, Mn-B Mn < 1.65 %

CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,37 to 0,44	from 0,10 to 0,40	from 0,50 to 0,80	0,045 max	0,045 max	0,40 max	Cr+Mo+Ni = < 0,63
Mo	Ni	B	Cu	Al	Pb	
0,10 max	0,40 max	-	0,30 max	-	-	

MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	16	-	-	580	16	-	-	-	-	-	-	-	-
16	100	-	-	550	17	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C40	C40	AF60C40	C40	40	-	C40
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
1040	S40C	070M40	-	-	40	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.