



STANDARD

CLASSIFICATION

FEATURES

UNI EN ISO 16120-2:2017

Steel rods, bars and wire for cold heading and cold extrusion - steels for quenching and tempering

Alloy special steel

C38D - Nr. 1.0516

B, Mn-B Mn < 1.65 %

CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,35 to 0,40	from 0,10 to 0,30	from 0,50 to 0,80	0,030 max	0,030 max	0,20 max	-
Mo	Ni	B	Cu	Al	Pb	
0,05 max	0,25 max	-	0,30 max	0,01 max	-	

MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	60	-	-	-	-	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C38D	C38D	FM 38	C 38 D	-	-	-
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
1035	SWRH 37	-	-	-	-	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.