Giuseppe & F.lli Bonaiti s.r.l.
a Socio unico
FILO DI ACCIAIO

C20D2 Nr. 1.1137

GENERAL PURPOSE STEEL

STANDARD

EN ISO 16120-4:2017
Non Alloy Steel Wire Rod For Conversion to Wire - general purpose wire rod

CLASSIFICATION

Non Alloy Steel

FEATURES

C20D2 - Nr. 1.1137
Steels with average C < 0,12% or Rm < 400 MPa

CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,18 to 0,23	0,30 max	from 0,30 to 0,50	0,02 max	0,025 max	0,10 max	N - 0,007 max

Mo	Ni	B	Cu	Al	Pb
0,05 max	0,10 max	-	0,15 max	0,01 max	-

MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	60	-	-	-	-	-	-	-	-	-	-	-	-

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN,WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
C20D2	C20D2	FM 20	C20 D 2	-	-	-

USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)
-	-	-	-	-	-

Data contained in this document are intended for reference only and may be subject to continuous changes.
Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.