



## STANDARD

## CLASSIFICATION

## FEATURES

**UNI EN 10263-4: 2017**

Non Alloy Steel Wire Rod For Conversion to Wire - wire rod for specials applications

*Non Alloy Steel*

**23MnB3 - Nr. 1.5507**

Structural pressure vessel and engineering steels with C < 0,5%

## CHEMICAL ANALYSIS

C	Si	Mn	P	S	Cr	Other
from 0,21 to 0,25	0,15 max	from 0,80 to 1,00	0,015 max	0,015 max	from 0,25 to 0,35	-
Mo	Ni	B	Cu	Al	Pb	
-	-	from 0,0008 to 0,005	0,25 max	-	-	

## MECHANICAL PROPERTIES

Diameter		As Hot Rolled (+U) or Rolled and peeled (+U +PE)		Annealed (+AC) or Annealed + Peeled (+AC +PE)		Cold Drawn (+U +C)		Cold Drawn and Annealed (+U +C +AC)		Cold Drawn then Annealed and Skin passed (+U +C +AC + LC)		Annealed and Cold Drawn (+AC +C)	
from	to	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min	Rm (Mpa) max	Z (%) min
2	5	-	-	-	-	-	-	510	66	550	64	-	-
5	10	600	60	520	64	700	55	500	66	540	64	620	59
10	25	600	60	520	64	690	55	500	66	540	64	610	59

In case of specific needs, contact our sales offices to evaluate feasibility and agree on the values of Rm.

## EQUIVALENT STEEL GRADES

EUROPE (EN)	GERMANY (DIN, WNr)	FRANCE (AFNOR)	ITALY (UNI)	CHINA (GB)	FINLAND (SFS)	INTERN (ISO)
23MnB3	23MnB3	-	-	-	-	-
USA (SAE)	JAPAN (JIS)	UK (BS)	SPAIN (UNE)	SWEDEN (SS)	RUSSIA (GOST)	
-	-	-	-	-	-	

Data contained in this document are intended for reference only and may be subject to continuous changes.

Giuseppe & F. lli Bonaiti SRL declines any and all responsibility for the consequences that may arise from their use.